



Acryl 100

ACRYL 100 is a water based paint for exterior and interior. Main features of **ACRYL 100** are: high coverage and hiding power, resistant to water, good vapour diffusion rate, and easy to apply. This velvet finishing paint leaves in the air a very light fresh lemon scent sensation due to a effective fungicide, preserving the wall from moulds formation. **ACRYL 100**, in interior is also a perfect base for **MILLELUCI** and **RUGIADA**.

COLOURS: White and tintosystem colours

SURFACE

PREPARATION:

New walls: apply one coat of **SAIFSEAL ACRYL 300%** (dilution by water: 300%).

Old walls: brush all flaking and dusty old paints, clean carefully and apply one coat of **SAIFSEAL DUR** (dilution 300% by water).

Old mouldy walls : first apply one or two coats of "**NO MOULD**". After drying, take out all dusty staff and proceed with one coat of **SAIFSEAL SAN** (mould inhibitor undercoat).

APPLICATION:

According to surface absorption, dilute from 20 to 30% by water. Mix the product thoroughly before application. Apply two coats by brush, power or airless spray-gun. Second coat dilution: 20%. Do not apply under + 5° C.. Acryl 100 is odourless, any way, keep windows open while the coat is drying.



Acryl 100

Linea Acryl

>ACRYL 100		N A 03
		REV 0
		05/11/2004
		SPEC. REF. A 03
TECHNICAL DATA		
Binding agent :	Modified acryl resin	
Specific weight:	1,56 kg /l \pm 2%	UNI 8910
pH:	8,5÷9,5	UNI 8311
Viscosity Brookfield:	48000 CPS a 20° C. S. 5 RPM $5 \pm 10\%$	UNI 8490
% Solid weight:	62,40% \pm 2	ISTR 0007
APPLICATION DATA		
Storage Temperature:	From +5°C to +40°C	
Application Temperature:	From +5°C to +35°C	
Shelf life:	Dry and fresh store, packed and sealed 18 months at least.	
Dilution:	20-30% water, according to substrate absorption .	
Drying Time:	1 hours touch dry. Recoatable after 4-6 hours.	
Consumption:	4/5 lt/mq	
Packing:	2,5 lt – 5 l - 10 lt - 15 lt.	

These data are result of scrupulous tests and are showing our most updated knowledge. These data are distributed as information and cannot be proof for a dispute since the application and conservation of the product may change not under our responsibility.