



Aries extra

ARIES EXTRA is a wall coating based on selected marble grains, coloured by iron pigments resistant to ultraviolet rays. Usually applied in exteriors, due to resistance to weather conditions, can be used in interiors, where a heavy duty coating is required.

ARIES EXTRA has an additional high permanent protection against mould formations after applications.

ARIES EXTRA is produced in two different types:

- **FINE - RLF** : 1,5 mm grain
- **MEDIUM - RLM** : 2 mm grain

COLOURS: 14 standard colours and "**I RESTAURI**" colour card .

WALL PREPARATION: New walls: apply one or two coats of coloured "**SAIFSEAL COAT QUARTZ**" ; (very absorbent walls require a previous coat of "**SAIFSEAL DUR 300%** ").
Old walls: take out all flaking, old paints by iron brush, clean the wall and apply one coat of "**SAIFSEAL DUR 300**" . Proceed with application of **SAIFSEAL COAT QUARTZ**.
Old mouldy walls: apply one or two coats of "**NO MOULD**". When dried, clean the surface taking out all dust, then proceed with **SAIFSEAL DUR** as consolidating primer, then apply **SAIFSEAL COAT QUARTZ** .

APPLICATION: mix thoroughly the product before application. Spread **ARIES EXTRA** on the wall using a stainless steel trowel. Take out all exceeding material keeping the trowel at a slight edge to the wall surface, in order to uniform the coating thickness. After 10 – 15 ' , just give a pass with the same trowel, to smooth any small defect on the wall, keeping always the trowel clean and damp.
Solvent free product, do not require special precautions during application. Do not apply under direct sun rays, during windy days; protect from rain at least for 24 hours after application. Do not apply when the temperature is expected to go below + 5° C.
Deep drying time: 72 hours .
Tools cleaning: warm water.



Aries extra

I rivestimenti

>ARIES EXTRA		N A 11
		REV 1
		05/11/2004
		SPEC. REF. A 11
TECHNICAL DATA		
Binding Agent:	Styro-acryl.	
Specific weight:	1,64 \pm 1% Kg/l	UNI 8910
pH:	8,5÷9,5	UNI 8311
Viscosity Brookfield:	250000 \pm 10% cps S=6 Rpm=0,5	UNI 8490
% Solid Weight:	82% \pm 2	ISTR 0007
APPLICATION DATA		
Storage temperature	From +5°C to +45°C	
Application Temperature:	From +5°C to +35°C	
Shelf life:	Dry and fresh store, packed and sealed 18 months at least.	
Dilution:	Ready to use.	
Drying Time:	3 hour touch dry. Recoatable after 96 hours.	
Consumption:	"F" 2,2 kg/m. "R" 3,2 kg/m.	
Packing:	5 kg - 25 kg	

These data are result of scrupulous tests and are showing our most updated knowledge. These data are distributed as information and cannot be proof for a dispute since the application and conservation of the product may change not under our responsibility.