



Madreperla

MADREPERLA is an interesting very smooth finish coat that creates light transparent and shaded effects, adding a precious pearlescent reflection. The decorative effect is astonishing, washability and scratch resistance is high, consumption is very low. **MADREPERLA** coat is very thin, it requires a good wall preparation: dry wall well prepared is a perfect substrate. **MADREPERLA** is perfect coat when delicate and refined Venetian stucco look is required, when a tough and non aging coat is needed, joined to an easy and fast application.

Two **MADREPERLA** type are available supplied as neutral color:

MADREPERLA SFUMATO: to be applied by sponge.

MADREPERLA STUCCO: to be applied by spatula.

Coloring doses are the same for both finishes, to be added to the proper base.

Colours marked by the reference/1, require one coloring dose; color marked by the reference/2 require two doses.

COLOURS: uncoloured, 80 standard colours available by tinting system or toners

SURFACE PREPARATION **Old and new wall:** one coat of **SAIFSEAL DUR 300%**.
One or two coats of **UNOcoat, Acryl 100 or MICROFINE**
MADREPERLA SFUMATO: **500,color R 1241** applied by brush or roller.

SURFACE PREPARATION **Old and new wall:** one coat of **SAIFSEAL DUR 300%**.
One or two coats of **MICRO 500,color R 1241** applied
MADREPERLA STUCCO : by brush or roller.

APPLICATION: **MADREPERLA SFUMATO** is ready use, to be coloured by tinting doses. Tinting machine formulas are available too. First add the pigmenting toner (one or two, according to color chosen) to **MADREPERLA SFUMATO**, mix thoroughly, apply one coat by brush, and immediately spread it on the surface by the sponge, until getting a uniform shaded effect before it dries. Due to low thickness, **MADREPERLA SFUMATO** dries fast; on large areas it is suggested to apply it by two operators: first one will apply by brush or roller the coat, second will follow immediately treating the wet surface by the sponge. For deeper effects a second coat can be applied, after few hours.

APPLICATION: **MADREPERLA STUCCO** is ready use, to be coloured by tinting doses. Tinting machine formulas are available too. Apply by spatula a thin coat of **MADREPERLA STUCCO**, avoiding trowel marks.



Madreperla

Stucchi perlescenti

When first coat is dry, apply second coat taking care to spread the product uniformly and smoothly. Final appearance will be a smooth surface showing soft shaded mother or pearl effects.

MADREPERLA, odourless water based coat, doesn't need special precautions during application. Just keep windows open to increase ventilation. Clean tools by soap and water immediately after use.

>MADREPERLA SFUMATO		N M 21
		REV 1
		22/10/2007
		SPEC. REF. M 21
TECHNICAL DATA		
Binding Agent:	Modified acryl resin	
Specific weight:	1,21 ± 1% Kg/l	UNI 8910
pH:	8,5÷9,5	UNI 8311
Viscosity Brookfield:	10000 CPS a 20° C. S. 5 RPM 5 ± 10%	UNI 8490
% Solids by Volume:	49,9% ± 2	ISTR 0007
APPLICATION DATA		
Storing Temperature:	From +10°C to +30°C	
Application Temperature:	From +10°C to +40°C	
Shelf life:	Dry and fresh store, packed and sealed 12 months at least.	
Dilution:	Ready to use	
Drying Time:	1 hour touch dry. Recoatable after 2 hours	
Consumption:	from 100 to 120 g/mq	
Packing:	15 l - 2,5 l - 0,750 l	

These data are result of scrupulous tests and are showing our most updated knowledge. These data are distributed as information and cannot be proof for a dispute since the application and conservation of the product may change not under our responsibility.



Madreperla

Stucchi perlescenti

>MADREPERLA STUCCO		N M 26
		REV 0
		22/10/2007
		SPEC. REF. M 26
TECHNICAL DATA		
Binding Agent:	Modified acryl resin	
Specific weight:	1,07 ± 1% Kg/l	UNI 8910
pH:	8,5÷9,5	UNI 8311
Viscosity Brookfield:	400000 CPS a 20° C. S. 7 RPM 2 ± 10%	UNI 8490
% Solids by Volume:	53,9% ± 2	ISTR 0007
APPLICATION DATA		
Storing Temperature:	From +10°C to +30°C	
Application Temperature:	From +10°C to +40°C	
Shelf life:	Dry and fresh store, packed and sealed 12 months at least.	
Dilution:	Ready to use	
Drying Time:	1 hour touch dry. Recoatable after 2 hours	
Consumption:	from 150 to 200 g/mq	
Packing:	15 l - 2,5 l	

These data are result of scrupulous tests and are showing our most updated knowledge. These data are distributed as information and cannot be proof for a dispute since the application and conservation of the product may change not under our responsibility.