



# Riflessi

**RIFLESSI** is a two-step application system resulting in a brilliant, matt finish. The ancient "Damascato texture", obtained by **RIFLESSI** in an extremely innovative design, is easily applied and results in a finish which is both washable and resistant.

**COLOURS:** Standard colours as showed in "RIFLESSI" catalogue.  
Other colours available from **TINTHOSYSTEM** colours card.

#### **SURFACE**

**PREPARATION:** **New walls:** apply one coat of **SAIFSEAL DUR 300%** diluted 300% water.  
**Old walls:** brush off all flaking paints, cracks should be filled out and sand papered. Then apply one coat of **SAIFSEAL DUR 300%** diluted 300% water.

**APPLICATION:** When the undercoat is dried, apply two coats of **RIFLESSI RX Base**, with a wool roller, insuring spread evenly. Wait few hours between coats. Allow the **RIFLESSI RX Base** surface to dry for six-eight hours until completely dry. Dilute the **RIFLESSI RY Finish** coat with 35 percent water. Using a natural sponge, apply the diluted **RIFLESSI RY Finish** coat to all surfaces coated by **RIFLESSI RX Base**.

It is important to apply the **RIFLESSI RY Finish** coat evenly, without overlapping each sponge design, and rotating the sponge before leaning it to the wall to insure a non-repetitive pattern.

Clean tools application after use with warm water



# Riflessi

Linea nuvole

<b>RIFLESSI RY</b>		N R 04
		REV 0
		05/11/2004
		SPEC. REF. R 04
<b>TECHNICAL DATA</b>		
Binding agent :	Styro acryl resin	
Specific weight:	1,45 kg /l $\pm$ 2%	UNI 8910
pH:	8,5÷9,5	UNI 8311
Viscosity Brookfield:	30000 CPS a 20° C. S. 5 RPM $\pm$ 10%	UNI 8490
% Solid weight:	59,8 $\pm$ 2	ISTR 0007
<b>APPLICATION DATA</b>		
Storage Temperature:	From +5°C to +45°C	
Application Temperature:	From +5°C to +35°C	
Shelf life:	Dry and fresh store, packed and sealed 18 months at least.	
Dilution:	50% water	
Drying Time:	2 hours touch dry. Recoatable after 6-8 hours	
Consumption:	0,050 l/mq	
Packing:	0,750 l – 2,5 l	

These data are result of scrupulous tests and are showing our most updated knowledge. These data are distributed as information and cannot be proof for a dispute since the application and conservation of the product may change not under our responsibility.



# Riflessi

Linea nuvole

<b>&gt;RIFLESSI RX</b>		N R 03
		REV 0
		05/11/2004
		SPEC. REF. R 03
<b>TECHNICAL DATA</b>		
Binding agent :	Styro acryl resin	
Specific weight:	1,32 kg /l $\pm$ 2%	UNI 8910
pH:	8,5÷9,5	UNI 8311
Viscosity Brookfield:	11.000 CPS a 20°C S.5 RPM 5 $\pm$ 10%	UNI 8490
% Solid weight:	59,8 $\pm$ 2	ISTR 0007
<b>APPLICATION DATA</b>		
Storage Temperature:	From +5°C to +45°C	
Application Temperature:	From +5°C to +35°C	
Shelf life:	Dry and fresh store, packed and sealed 18 months at least.	
Dilution:	3-5% water	
Drying Time:	2 hours touch dry. Recoat after 6-8 hours	
Consumption:	from 7 to 8 mq/lt two coats	
Packing:	0,750 l – 2,5 l - 15l	

These data are result of scrupulous tests and are showing our most updated knowledge. These data are distributed as information and cannot be proof for a dispute since the application and conservation of the product may change not under our responsibility.